

Low temperature specific heat of glasses : A non-extensive approach

Ashok Razdan

Nuclear Research Laboratory

Bhabha Atomic Research Centre

Trombay, Mumbai- 400085

Abstract :

Specific heat is calculated using Tsallis Statistics. It is observed that it is possible to explain some low temperature specific heat properties of glasses using non-extensive approach. A similarity between temperature dependence of non-extensive specific heat and fractal specific heat is also discussed.

Motivation:

Non-extensive statistics is being increasingly used to explain anomalous behaviour observed in the properties of various physical system. Tsallis statistics has been used to study physical systems /phenomena which include turbulence in plasma [1], Cosmic ray background radiation [2], self gravitating systems [3], econo-physics[4], electron -positron annihilation [5], classical and quantum chaos [6], linear response theory [7], Levy type anomalous super diffusion [8], thermalization of electron - phonon systems [9], low dimensional dissipative systems [10] etc. It has been shown that non-extensive features get manifested in those systems which have long range forces, long memory effects or in those systems which evolve in (non Euclidean like space-time) fractal space time [11 and reference therein]. Apart from other applications it has been suggested [11] that non-extensive statistics can be applied to complex systems like glassy materials and fractal / multi-fractal or unconventional structures also. Anomalous low temperature specific heat results in glasses have motivated us to use non-

extensive statistics. We will also compare specific heat using Tsallis statistics with specific heat of a fractal.

Low temperature specific heat:

Specific heat depends on density of states $g(\omega)$

$$C_p = \frac{k_B^2}{\hbar} \int_0^\infty g\left(\frac{k_B T}{\hbar} x\right) \frac{x^2 e^x}{(e^x - 1)^2} dx \quad (1)$$

where $x = \frac{\hbar\omega}{k_B T}$. Above equation has been obtained using Boltzmann Gibbs statistical mechanics. Glasses at low temperature (below 2K) show quasi-linear behaviour i.e. approximate linear dependence on temperature T. Again glassy systems do not follow T^3 dependence even above 2K as in some cases maximum in $\frac{C_p}{T^3}$ is observed. Above properties are universal features of glassy systems [12,13]. Another interesting feature is $\frac{C_p}{T}$ dependence on T^2 for crystals and glassy phase of the same systems [14].

Theory :

Non-extensive statistics is based on two postulates [11 and reference therein]. First is the definition of non-extensive entropy

$$S_q = \frac{1 - P_i^q}{q - 1} \quad (2)$$

where q is the non-extensive entropic index and P_i are the probabilities of the microscopic states with $\sum P_i = 1$.

The second postulate is the definition of energy $U_q = \sum P_i^q E_i$, where E_i is the energy spectrum. As $q \rightarrow 1$, $S_q = - \sum p_i \ln P_i$, which is the Boltzmann Gibbs Shannon entropy.

To derive non-extensive form of specific heat we have to use non-extensive quantum distribution function of bosons. It is very difficult to derive exact analytical expression for non-extensive distribution function. However, there are many studies which provide the approximate form of non-extensive distribution functions [2,15]. In the present paper we use dilute gas approximation (DGA) for boson distribution function. For DGA case, the average occupation number is given as [15]

$$\langle n_q \rangle = \frac{1}{(1 + (q - 1)\beta(E_i - \mu)^{\frac{1}{q-1}} - 1)} \quad (3)$$




Figure 1: Non-extensive specific heat for various values of q ; $q=1.5(a), 1.6(b), 1.7(c), 1.8(d), 1.9(e), 2.0(f), 2.5(g), 3.0(h), 3.5(k)$

When dealing with system in contact with the heat bath at the temperature β , we have

$$\langle n_q \rangle = \frac{\hbar\omega_i}{(1 + (q-1)\frac{\hbar\omega_i}{kT})^{\frac{1}{q-1}} - 1} \quad (4)$$

Averaged over non-extensive distribution, expectation value of energy is

$$\langle E_q \rangle = \hbar\omega \langle n_q \rangle \quad (5)$$

and total vibrational energy is

$$U_q = \int \hbar\omega \langle n_q \rangle g(\omega) \quad (6)$$

from which specific heat can be obtained

$$C_p = \frac{\partial U_q}{\partial T} \quad (7)$$

For the case of Debye approximation $g(\omega) \propto (\omega)^2$. Equation (7) represents specific heat using Tsallis statistics where n_q is given by equation (4).

Results and Discussion :

We have numerically solved equation (7) using equations (4) and (6), for various values of q . It is very clear from figure 1 that quasi-linear behaviour or maxima in $\frac{C_p}{T^3}$ is not explained by including non-extensive statistics. Various curves in figure 1 have been obtained for fixed value of Debye temperature




Figure 2: Fig2a: Sp. heat data corresponding to $(B_2O_3)_{100-x}(Na_2O)_x$ for different % of Na_2O [16,17,18] Fig2b: Sp. heat data corresponding to glassy alcohols [14,19]. In y-axis $\frac{c_p}{T}$ is plotted against T^2 in x-axis

($\theta_D=300$ K). The shape and nature of curves in figure 1 is decided by value of q . A linear display of specific heat versus T^2 dependence is followed in glasses as depicted in figure 2a and figure 2b. In figure 2a we are plotting experimental data corresponding to $(B_2O_3)_{100-x}(Na_2O)_x$ taken from reference [16,17,18]. The data with (+) sign corresponds to 0 % of Na_2O , (*) corresponds to 1 % of Na_2O , hollow square corresponds to 6 %, filled square corresponds to 16 % and crosses (x) corresponds to 25 % of Na_2O respectively. The fitted curves correspond to different values of q from (+) onwards are $q=5.5, 5.0, 4.5, 3.5, 3.0, 2.9, 2.7, 2.6$ respectively. The slope of experimental data in figure 2a is strongly dependent on presence, absence or excess of Na_2O in glassy system. Non-extensive specific heat seems to explain data in figure 2a for different values of q . Again in figure 2b specific heat data of various glassy systems show strong dependence on slope and can be explained by non-extensive approach. The experimental data in fig2b corresponds to glassy alcohols like 2-propanol (+), filled square to D-ethonal, cross (x) to D-ethonal (OG, orientational glass), hollow square to 1-propanol and star (*) to glycerol respectively. The corresponding fitted q -values are $q=2.8, 2.65, 2.62, 2.60$ and 2.25 respectively. The experimental data has been taken from reference [19,22]. It is interesting to mention here that a




Figure 3: Comparison of non-extensive specific heat with fractal specific heat. In y-axis $\frac{c_p}{T}$ is plotted against T^2 in x-axis

strong slope dependence of specific heat on T^2 has been used to [14] depict two different phases of crystal and glasses with two different Debye temperatures.

Low temperature specific heat studies in silica aerogels and other disordered systems do not follow Debye model and concepts of fractals have been used to explain such results [20]. For a fractal approach density of states $g(\omega) \propto \omega^{\tilde{d}}$ where $\tilde{d}$ is spectral dimension.

We have plotted proportional temperature dependence of specific heat of a fractal in figure 3. Curves b,d and e correspond to $\tilde{d}=3.8, 2.8$ and 1.8 whereas curves a,b and f correspond to $q=1.7, 1.65$ and 1.6 respectively. It is evident from figure 3 that there is lot of similarity between fractal and non-extensive specific heat. The similarity between these curves is expected because non-extensive statistics corresponds to non-Euclidean space time which is fractal in nature. The similarity between fractal and nonextensive results were also reported for Lamb Mossbauer factor [21]. It has been shown that magnetic properties of manganites [23] and their corresponding phase diagrams [24] can be explained in the framework of Tsallis statistics.

Some of the anomalous properties have been explained by using soft potential model which is an extension of tunnelling model in which group of atoms can tunnel between same energy configurations [14]. Recently it has been re-

ported that quasi-linear behaviour or maximum in specific heat data of various incommensurate phases can be explained [25] by considering effect of phason damping.

References:

1. B.M.Boghosian, Phys. Rev. E 53(1996)4745
2. C.Tsallis, F.C. Sa Barreto and E.D.Loh, Phys. Rev. E 52(1995) 1447
3. V.H.Hamity and D.E.Barraco, Phys. Rev. Lett. 76(1996)4664
4. C.Tsallis, C.Anteneodo, L.Borland and R.Osorio, cond-mat/0301307
5. I.Bediaga, E.M.F.Curado and J. Miranda, Physica A 286(2000)156
6. C.Tsallis, A.R.Plantino and W. -M.Zheng, Chaos,Solitons and Fractals 8(1997)885,
Y.Weinstein, S.Lloyd and C.Tsallis, Phys. Rev. Lett. 89(2002)214101
7. A.K.Rajagopal, Phys. Rev. Lett. 76(1996) 3496
8. C.Tsallis, S.V.F. Levy, A.M.C.Souza and R.Maynard, Phys. Rev. Lett. 75(1995)3589
9. I.Koponen, Phys. Rev. E 55(1997)7759
10. M.L.Lyra and C.Tsallis, Phys. Rev. Lett. 80(1998)53
11. C.Tsallis, Physica A 221(1995)277-290,
C.Tsallis, R.S.Mendes, A.R.Plantino, Physica A 261(1998)534
12. W.A.Phillips, editor Amorphous Solids: Low Temperature Properties, Springer Berlin 1981
13. W.A.Phillips, Rep. Prog. Phys. 50(1987)1657
14. M.A.Ramos, C.Talon and S.Vieira, Phys. Rev. B 66(2002)01 2201
15. Q.A.Wang and A.Le Mehaute, Phys. Lett. A 242(1998)301

16. E.S.Pinango, M.A.Ramos, R.Villar and S.Vieira, in Basic Features of glassy State; Edited by J.Colmenero and A.Alegria (Singapore: World Scientific),pp. 509-513
17. M.A.Ramos and U.Buchenau 1998, Tunnelling Systems in Amorphous and Crystalline Solids, Edited by P.Esquinazi (Berlin:Springer) chapter 9,pp-527-569
18. M.A.Ramos cond-mat/0405055
19. M.A.Ramos, C.Talon and S.Vieira cond-mat/0201560 v1
20. A.M.de Goer, R.Calemczuk, B.Slace, et al Phys. Rev. B 40(1989)8327
21. A.Razdan, Phys. Lett. A 321(2004)190
22. M.A.Ramos, C.Talon, R. J. Jimenez-Rioboo and S. Vieira, J. Phys: Condens. Matter 15(2003)S1007
23. V.S.Amaral, E.K.Lenzi and I.S. Oliveira, Phys. Rev. B 66(2002)134417
24. M.S.Reis, V.S.Amaral, J.P. Araujo and I.S. Oliveira, Phys. Rev. B 68(2004)014404
25. A.Cano and A.P.Levanyuk, Phys. Rev. Lett. 93(2004)245902